

Flexible layflat PVC hose, with polyester yarn reinforcement resistant to elongation, for pressurized delivery of liquids in general.



- 
SMOOTH SURFACE
\*\*\*\*\*

---

- 
FLEXIBILITY
\*

---

- 
ABRASION RESISTANCE
\*\*\*

---

- 
TEMPERATURE RANGE
-5 °c 60 °c

---

- 
CHEMICAL RESISTANCE
PVC Table

---

- 
CRUSHING RESISTANCE
\*

Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	working pressure at 23° bar	working press. at 40° bar	working press. at 60° bar	bursting press. at 23° bar	total thickness mm	weight meter g/m	# wires for angle n° x a°	working resistance kg	tensile breaking load kg	coil length m	Availability
20		20	23	8.5	7	4	25.5	1.5	135	28x70°	85	230	50/100	In stock
25	1	25	28	8.5	7	4	25.5	1.5	155	28x72°	96	260	50/100	In stock
32	1 1/4	32	35	8.5	7	4	25.5	1.5	210	28x75°	127	345	50/100	In stock
35		35	38	8.5	7	4	25.5	1.5	220	32x75°	138	375	50/100	In stock
38	1 1/2	38	41	8.5	7	4	25.5	1.5	240	32x75°	160	430	50/100	In stock
40		40	43	8.5	7	4	25.5	1.5	250	32x75°	160	435	50/100	In stock
45	1 3/4	45	48	6.5	5	2.5	19.5	1.5	280	36x78°	180	490	50/100	In stock
51	2	51	54	6.5	5	2.5	19.5	1.5	320	36x75°	190	515	50/100	In stock
60		60	64	6.5	5	2.5	19.5	2	370	48x76°	350	950	50/100	In stock
63	2 1/2	63.5	67.5	6.5	5	2.5	19.5	2	420	48x75°	370	1000	50/100	In stock
70		70	74	5.5	4	2	16.5	2	450	48x75°	415	1120	50/100	In stock
76	3	76	80	5.5	4	2	16.5	2	520	60x75°	460	1250	50/100	In stock
80		80	84	5.5	4	2	16.5	2	580	60x80°	480	1300	50/100	In stock
90	3 1/2	90	94	5.5	4	2	16.5	2	660	60x78°	540	1470	50/100	On demand
102	4	102	106	5.5	4	2	16.5	2	720	72x78°	605	1640	50/100	In stock
110		110	115	5.5	4	2	16.5	2.5	780	72x78°	1130	1800	50/100	In stock
127	5	127	132	3	2	0.5	9	2.5	1130	72x78°	800	2150	50/100	In stock
152	6	152	157	3	2	0.5	9	2.5	1350	72x78°	815	2200	50/100	In stock
204	8	204	209	2.5	1.5	0.3	7	2.5	2000	120x80°	780	2100	50	In stock