



PRODOTTO TIVAR DRY SLIDE

TIPOLOGIA MATERIALE PLASTICO

N° SCHEMA 1154

Thanks to the lubricant built into a PE-UHMW matrix with higher molecular weight, **TIVAR DrySlide** offers a lower coefficient of friction and enhanced wear and abrasion resistance than TIVAR 1000. The additives used also make this material static dissipative and considerably improve UV-resistance.

ULTRA HIGH MOLECULAR WEIGHT POLYETHYLENE [PE-UHMW + internal lubricant + other additives]

| PROPERTIES | Test methods | Units | VALUES |
|--|---------------|-----------------------|------------------------|
| Colour | - | - | black |
| Average molar mass (average molecular weight) - (1) | - | 10 ⁶ g/mol | 9 |
| Density | ISO 1183-1 | g/cm ³ | 0.935 |
| Water absorption at saturation in water of 23 °C | - | % | < 0.1 |
| Thermal Properties (2) | | | |
| Melting temperature (DSC, 10 °C/min) | ISO 11357-1/3 | °C | 135 |
| Thermal conductivity at 23 °C | - | W/(K.m) | 0.40 |
| Average coefficient of linear thermal expansion between 23 and 100 °C | - | m/(m.K) | 200 x 10 ⁻⁶ |
| Temperature of deflection under load: | | | |
| - method A: 1.8 MPa | ISO 75-1/-2 | °C | 42 |
| Vicat softening temperature - VST/B50 | ISO 306 | °C | 80 |
| Max. allowable service temperature in air: | | | |
| - for short periods (3) | - | °C | 120 |
| - continuously : for 20,000 h (4) | - | °C | 80 |
| Min. service temperature (5) | - | °C | -150 |
| Flammability (6): | | | |
| - "Oxygen Index" | ISO 4589-1/-2 | % | < 20 |
| - according to UL 94 (6 mm thickness) | - | - | HB |
| Mechanical Properties at 23 °C (7) | | | |
| Tension test (8): | | | |
| - tensile stress at yield (9) | ISO 527-1/-2 | MPa | 18 |
| - tensile strain at yield (9) | ISO 527-1/-2 | % | 20 |
| - tensile strain at break (9) | ISO 527-1/-2 | % | > 50 |
| - tensile modulus of elasticity (10) | ISO 527-1/-2 | MPa | 650 |
| Compression test (11): | | | |
| - compressive stress at 1 / 2 / 5 % nominal strain (10) | ISO 604 | MPa | 6 / 10 / 16 |
| Charpy impact strength - unnotched (12) | ISO 179-1/1eU | kJ/m ² | no break |
| Charpy impact strength - notched | ISO 179-1/1eA | kJ/m ² | 100P |
| Charpy impact strength - notched (double 14 notch) - (13) | ISO 11542-2 | kJ/m ² | 130 |
| Ball indentation hardness (14) | ISO 2039-1 | N/mm ² | 32 |
| Shore hardness D (14) | ISO 868 | - | 59 |
| Relative volume loss during a wear test in "sand/water slurry"; TIVAR 1000 = 100 | ISO 14597 | - | 85 |
| Electrical Properties at 23 °C | | | |
| Electric strength (15) | IEC 60243-1 | kV/mm | - |
| Volume resistivity | IEC 60093 | Ohm.cm | - |
| Surface resistivity | IEC 60093 | Ohm | < 10 ⁸ |
| Relative permittivity ϵ_r :- at 100 Hz | | | |
| - at 1 MHz | IEC 60250 | - | - |
| Dielectric dissipation factor tan δ :- at 100 Hz | | | |
| - at 1 MHz | IEC 60250 | - | - |
| Comparative tracking index (CTI) | IEC 60112 | - | - |

Legend:

- (1) This is the average molar mass of the PE-UHMW resins (irrespective of any additives) used for the manufacture of this material. It is calculated by means of the Margolies-equation $M = 5.37 \times 10^4 \times [\eta]^{1.49}$, with $[\eta]$ being the intrinsic viscosity (Staudinger index) derived from a viscosity measurement according to ISO 1628-3:2001, using decahydronaphthalene as a solvent (concentration of 0.0002 g/cm³).
- (2) The figures given for these properties are for the most part derived from raw material supplier data and other publications.
- (3) Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- (4) Temperature resistance over a period of 20,000 hours. After this period of time, there is a decrease in tensile strength - measured at 23 °C - of about 50 % as compared with the original value. The temperature value given here is thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- (5) Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically mainly determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
- (6) These estimated ratings, derived from raw material supplier data and other publications, are not intended to reflect hazards presented by the material under actual fire conditions. There is no 'UL File Number' available for TIVAR DrySlide stock shapes.
- (7) The figures given for these properties are average values of tests run on test specimens machined out of 20 - 30 mm thick plates.
- (8) Test specimens: Type 1 B
- (9) Test speed: 50 mm/min
- (10) Test speed: 1 mm/min.
- (11) Test specimens: cylinders Ø 8 mm x 16 mm
- (12) Pendulum used: 15 J
- (13) Pendulum used: 25 J
- (14) Measured on 10 mm thick test specimens.
- (15) Electrode configuration: Ø 25 / Ø 75 mm coaxial cylinders ; in transformer oil according to IEC 60296 ; 1 mm thick test specimens.

This table, mainly to be used for comparison purposes, is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties. **However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.**

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.